

ENGUARD® BP 72 A Multi Purpose Bonding Paste

ENGUARD BP 72 A is a pre-accelerated bonding paste based on unsaturated polyester resin, with good mechanical properties. ENGUARD BP 72 A has a low filler content and a high thixotropy level avoiding sagging and making application easy.

Typical properties of bonding paste

Property at 23 °C	Value	Unit	Method
Density	1,2	kg/dm ³	ISO 2811
Geltime, 2% MEKP-50	10	min	D 006
Hardening time, 2% MEKP-50	3	hours	QC 36
Complete hardening	72	hours	

Typical properties of cured bonding paste

Property	Value	Unit	Method
Tensile strength	30	MPa	ASTM C297
Shear strength	29	MPa	R 028
Compression strength	142	MPa	R 029
Hardness	30	Barcol	ASTM D2583

Application and use

ENGUARD BP 72 A bonding paste is suitable for use in the marine, building/sanitary, tanks/silos and transport/panel industry. ENGUARD BP 72 A is used for adhesion of polyester laminates and/or adhesion of polyester laminates to balsa, PVC or PU foam in sandwich structures.

Recommended thickness of bonding paste is 0,3-3 mm and bonding paste must not start gelling before parts are attached together. Mechanical forces on bonded parts must not be used within three days from application.

Remark: Temperature of workshop, raw materials and tools should be 18-25°C and relative humidity below 70%. Surfaces to be bonded must be cleaned eg. with acetone or by grinding. A high quality methyl ethyl ketone peroxide (MEKP) should be used between 1-2%. The bonding paste with catalyst must be stirred well before use.

Certificates and approvals

The manufacturing, quality control and distribution of products, by Ashland Composite Polymers, are complying with one or more of the following programs or standards: Responsible Care, ISO 9001, ISO 14001 and OHSAS 18001 by BVQI.

Handling and storage

Shelf life of bonding paste is 5 months from the day of manufacture and it is highly recommended that all material is stored at stable temperature under 25 °C preferably indoors and away from direct sunlight.



Ashland is committed to continuous evolution of technology and service solutions that promote health, safety and environmental protection around the world.

® Registered trademark and ™ trademark of Ashland Inc.
* Registered service mark of the American Chemistry Council
© Ashland Inc. All rights reserved.

ENGUARD® BP 72 A Multi Purpose Bonding Paste

Notice

All information presented herein is believed to be accurate and reliable, and is solely for the user's consideration, investigation and verification. The information is not to be taken as an express or implied representation or warranty for which Ashland assumes legal responsibility. Any warranties, including warranties of merchantability or non-infringement of intellectual property rights of third parties, are herewith expressly excluded.

Since the user's product formulations, specific use applications and conditions of use are beyond the control of Ashland, Ashland makes no warranty or representation regarding the results which may be obtained by the user. It shall be the responsibility of the user to determine the suitability of any of the products mentioned for the user's specific application.

Ashland requests that the user reads, understands and complies with the information contained herein and the current Material Safety Data Sheet.

More information

Ashland Composite Polymers
European Headquarters
C / Frederic Mompou 5, 4 th Floor
08960 Sant Just Desvern
SPAIN
Phone: +34 93 206 51 20
Fax: +34 93 204 13 02



Ashland is committed to continuous evolution of technology and service solutions that promote health, safety and environmental protection around the world.

® Registered trademark and ™ trademark of Ashland Inc.
* Registered service mark of the American Chemistry Council
© Ashland Inc. All rights reserved.