

MAXGUARD® GT // H Premium Tooling Gelcoat

MAXGUARD GT // H premium tooling gelcoat is based on epoxy modified vinyl ester. The base resin in combination with the gelcoat formula give final tooling a hard and glossy surface with good mechanical properties and toughness. MAXGUARD GT // H tooling gelcoat is available in black (75200) and green (75400) colours.

Typical liquid gelcoat properties at 23 °C

Property	Value	Unit	Method
Viscosity, Brookfield RV5, 10 rpm	10000	mPas	L 002
Viscosity, cone&plate	850	mPas	L 004
Geltime, 2% MEKP-50	20	min	L 005

Typical cured gelcoat properties

Property	Value	Unit	Method
Heat deflection temperature	110	°C	ISO 75 (A)
Hardness	35-40	Barcol	ASTM D2583

Application and use

MAXGUARD GT // H is a premium tooling gelcoat for brush application. It is suitable for manufacturing of tooling used in the marine, transportation and building and construction industries.

To achieve best results, temperature of all equipment, materials and work shop must be 20-26°C. If the temperature is too low the tooling gelcoat may be undercured (which can also occur if gelcoat layer is too thin or peroxide dosing is incorrect) and a hard glossy surface cannot be achieved.

Some guidelines;

- Stir the tooling gelcoat gently in the original pail.
- Take the needed quantity of gelcoat into a large enough pail to be able to add 2% of peroxide and mix peroxide thoroughly into the gelcoat.
- A brush grade (H or HH) has to be applied (with a high quality brush) in two layers. Apply a brush grade gelcoat very carefully to get even layers without sagging and air bubbles. The gelcoat must be allowed to cure between the layers for 3-6 hours, to form a sticky surface which does not give colour if touched with fingertips
- The final thickness of the cured tooling gelcoat should be 0,8 mm.



Ashland is committed to continuous evolution of technology and service solutions that promote health, safety and environmental protection around the world.

© Registered trademark and ™ trademark of Ashland Inc.
 * Registered service mark of the American Chemistry Council
 © Ashland Inc. All rights reserved.

MAXGUARD® GT // H Premium Tooling Gelcoat

Certificates and approvals

The manufacturing, quality control and distribution of products, by Ashland Composite Polymers, are complying with one or more of the following programs or standards: Responsible Care, ISO 9001, ISO 14001 and OHSAS 18001 by BVQI.

Handling and storage

For good working practices, see Ashland's "Gelcoat Handling Guide". Maximum storage of gelcoat is 3 months at temperature under 25°C away from direct sunlight. The gelcoat must be gently stirred before use. Temperature of workshop, raw materials and tools should be 20 - 26°C and relative humidity below 70%.

Notice

All information presented herein is believed to be accurate and reliable, and is solely for the user's consideration, investigation and verification. The information is not to be taken as an express or implied representation or warranty for which Ashland assumes legal responsibility. Any warranties, including warranties of merchantability or non-infringement of intellectual property rights of third parties, are herewith expressly excluded.

Since the user's product formulations, specific use applications and conditions of use are beyond the control of Ashland, Ashland makes no warranty or representation regarding the results which may be obtained by the user. It shall be the responsibility of the user to determine the suitability of any of the products mentioned for the user's specific application.

Ashland requests that the user reads, understands and complies with the information contained herein and the current Material Safety Data Sheet.

More information

EUROPEAN HEADQUARTERS
C/Numancia 185 8º 1a
08034 Barcelona
SPAIN

Phone: +34 93 206 51 20
Fax: +34 93 204 13 02



Ashland is committed to continuous evolution of technology and service solutions that promote health, safety and environmental protection around the world.

© Registered trademark and ™ trademark of Ashland Inc.
* Registered service mark of the American Chemistry Council
© Ashland Inc. All rights reserved.